

भारतीय पैकेजिंग संस्थान
INDIAN INSTITUTE
OF PACKAGING



E-2, MIDC AREA, POST BOX NO. 9432, ANDHERI (EAST), MUMBAI - 400 091
Phones : 2821 9803 / 2821 9469 / 2821 6751

FAX : 91-22-2837 5302 / 2825 4631 E-Mail : ip@bom4.vsnl.net.in • URL - <http://www.ip-in.com>

LABORATORY TEST REPORT

Forms / Formats, Issue-1, Rev.1 date 29-11-03
Title: Test Report

Form Format No. 1
Page 1 of 2
Date: 11th September, 06

Test Report No: 1/625/06/LAB/M-6

1. Title of the test: Compression Strength

2. Sample received from: M/s. Aashhish Pillast,

a) Name & Address: S.No. 114 / 1 - 2, New Urse Road,
Vadgaon Maval,
Tal. Maval,
Pune - 412 106

b) Contact Person: -

3. Ref. No. & Date: -

4. Sample Details: One sample said to be ABS Door material of Size 230 mm x 156 mm x 30 mm
with PUF Insulation

5. Sampling Plan: Sampling done by the party

6. Environmental Test Condition: $27 \pm 1^\circ\text{C}$ & $65 \pm 2\%$ RH

7. Test / Results:

Tested As Per

1. Flat Compression Strength (kgf) Ave 4501.8 at 1 mm deflection was observed and test was discontinued

IS 7028 - 1987 - 2.1.1

8. Test Specification:

N. C. Saha
N. C. SAHA
PROFESSOR
LABORATORY DIVISION

ve

Tested by NIBL/Prepar.

Asst. / Dy. / Jt. Director